



Tips on restoring dull Plastic Headlights

Depending on how dull they are. How much “DEAD” Plastic must be removed determines the grit of sandpaper you start with. If they are very dull start out with 800 grit by hand (wet) then 1000, 1500, 2000, and 3000. If you jump from course sandpaper to fine paper too quick it will take more time and labor. The finer the grit the more clear the finish will look. Using a DA with a soft interface pad will be much faster. The main point is to get to a 2000 or 3000 finish before applying 3 coats of ACL-3510 Axis Lightning clear over them. Apply 3 coats allowing 2 min. between coats.

Robert Coker
Technical Representative
Vogel Automotive Coatings
Cell # 606-304-1238