



Tips on the usage of ACL-7200 Uro Absolute Clear

2:1 mix Ratio No reduction necessary!

Will spray nicely thru a 1.3 or 1.4 Tip

Fast Activator will work well in temps up to the mid 70's

Only 2 coats necessary if not sanding and buffing.

If sanding (leveling) and buffing, we recommend 3 coats for long term durability.

Ready to sand and buff after 16-18 hr @ 75°

Robert Coker
Technical Representative
Vogel Automotive Coatings
Cell # 304-1238