



Tips on ACL-1210 Mirror Clear Quick Set II

Can be mixed 4:1 or 4:1: ½ Your Choice

Can be sprayed thru 1.3 or 1.4 Tip Your Choice

2 or 3 coats. If you chose 2 and then sand and buff, not enough film build will be left for long term durability.

If sanding and buffing 3 coats are strongly recommended!

At 85° and above, use Overall Activator.

***Robert Coker
Technical Representative
Vogel Automotive Coatings
Cell # 606-304-1238***