



APR12121-1

1K PRIMER SURFACER GRAY

PRODUCT# DESCRIPTION

APR12121-1 1K PRIMER SURFACER GRAY

DESCRIPTION

APR12121-1 Acrylic Primer Surfacers is fast drying, easy sanding primer surfacer that offers good adhesion, fast filling characteristics, outstanding feather-edge characteristics and color holdout.

MIXING

Mix: 1 part APR12121-1 & 1 part Premium Lacquer Solvent

APPLICATION

1. Spray at 8-9 psi at the cap for HVLP or 40-45 psi for conventional guns.
2. Apply 2-3 wet coats allowing 5-10 minutes flash time between coats.

DRYING

May be sanded in 15-20 minutes. Excessive film build and cool temperatures will extend dry times.

Final Sanding

To Seal: P400 Grit*

To Topcoat: P600 Grit*

* or equivalent

SUBSTRATES

Treated Steel*, Fiberglass, Cured Body Filler, Treated Aluminum, OEM Enamels, OEM Lacquers, Refinish Lacquers, Refinish Enamels, Metal Etches.

*Steel must be treated with an Etching Primer or Metal Etch.

TECHNICAL DATA

4.59 pounds per gallon

Pot life is unlimited.

Manufacturer's Exclusive Limited Warranty

For Industrial use only by professional, trained personnel using proper safety protective equipment. Not for sale to, or use by, the general public. Manufacturer warrants that its products are free from defect in material and workmanship at the time of sale. In the event that any product is proved by objective testing and analysis to have been defective at the time of sale, upon the return of the defective product, the manufacturer shall replace the product at no cost, excluding the shipping costs, as the exclusive remedy. This warranty does not cover damage caused by accident, misuse, improper application, improper combination of products or tampering. ALL IMPLIED WARRANTIES WHETHER IT BE OF MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. THIS WARRANTY EXCLUDES ALL INCIDENTAL AND CONSEQUENTIAL DAMAGES.

NOTE: Products are not recommended for use in temperatures below 60° F.

Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY

Read SDS Before Use

Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions. The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public. **SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.**